

## “DEFINITION OF A RADIANT BARRIER”

The Reflective Insulation Manufacturers Association (RIMA) recognizes and supports the ASTM standards for radiant barriers specifically ASTM C1313, ASTM C1158, and ASTM C168. Radiant barriers function by reducing heat transfer by radiation. The thermal performance or the reduction of radiant heat transfer is directly proportional to the surface emittance of the radiant barrier material. Emittance measurements of all materials range between zero (0), no radiant heat transfer, and one (1) that of a black surface or complete radiant heat transfer. Common building materials, such as wood, masonry, and fiberglass insulation have surface emittances of approximately 0.85 and therefore have high radiant heat transfer rates. Products defined as radiant barriers have surface emittances less than or equal to 0.1 or low radiant heat transfer rates. For more information visit the RIMA website [www.rima.net](http://www.rima.net) or call 1-800-279-4123

---

Reflective Insulation Manufacturers Association (RIMA)  
4519 E. Lone Cactus Drive  
Phoenix, Arizona 85050  
Toll-Free: 800/279-4123  
Fax: 480/513-4748  
E-Mail: [rma@rma.net](mailto:rma@rma.net)  
[www.rima.net](http://www.rima.net)

*The Reflective Insulation Manufacturers Association (RIMA), its members, and/or agents, make no guarantee as to, and assume no responsibility for, the correctness, sufficiency or completeness of the information contained herein. The information provided herein is intended to be a guide to the concept and applications of reflective insulation.*

TB #102  
10/01

Copyright 2001 by the Reflective Insulation Manufacturers Association